

Nano-Scale Confinement in Superconductors: A Scanning Tunneling Spectroscopy Study

Ch. Brun¹, T. Cren¹, L. Serrier-Garcia¹, S. Pons¹, V. Cherkez¹, D. Fokin², F. Debontridder¹,

and D. Roditchev^{*1,3}

¹Institut des Nanosciences de Paris, Université Pierre et Marie Curie UPMC and C.N.R.S.-UMR 7588,
4 place Jussieu, 75252 Paris, France.

²Joint Institute for High Temperatures, RAS 125412, Moscow, Russia.

³LPEM-UMR8213/CNRS-ESPCI ParisTech-UPMC, 10 rue Vauquelin-75005 Paris, France.

dimitri.roditchev@insp.jussieu.fr

The most famous macroscopic quantum phenomenon - superconductivity - is characterized by a nanometer-length scale, called coherence length ξ , at which the superconducting condensate may continuously evolve in space. The confinement of a superconducting material to scales comparable to ξ should substantially modify the superconducting properties. We addressed the problem of confinement in superconductivity by choosing a quasi-ideal model system – Pb atoms deposited in-situ on atomically clean surface of Si(111). Depending on growth conditions, we are able to produce superconducting Pb-nano-crystals of various sizes and shapes, but also to reach the ultimate thickness limit when only a single atomic layer of Pb exists at Si-surface. We studied the superconductivity in these artificial materials by Scanning Tunneling Spectroscopy in UHV at low temperatures down to 0.3K, and under magnetic fields up to 8T.

We will first discuss the simplest case of a vortex lattice weakly confined in relatively large superconducting samples $D \approx 10\xi$. We will show how the increasing confinement influences the vortex lattice, leading to novel ultra-dense configurations, impossible in bulk superconductors [1]. At even higher confinement, $D \approx 3-4\xi$, the Giant Vortices - quantum tornados characterized by a multiple phase accumulation $L \times 2\pi$, $L = 2; 3; 4$ - are experimentally revealed, and their unusual cores probed [2].

In the second part of the lecture we will discuss the electron confinement effects, i.e. the cases when the carriers are spatially confined to kF^{-1} . We will present how the superconductivity evolves with the reduction of Pb-film thickness down to a single atomic layer limit [3]. In the latter case, the electronic properties become extremely sensitive to the precise structure of the Pb/Si interface, and may result in an insulating, metallic or superconducting behaviour. In superconducting samples, such tiny and usually 'inoffensive' defects as single atomic surface steps or stacking faults disrupt the superconducting order. The samples become a nanometer-scale network of atomic superconducting terraces weakly connected by native Josephson links at steps and stacking faults.

[1] Cren, T., et al., Phys. Rev. Lett. 102, 127005 (2009).

[2] Cren, T., Serrier-Garcia L., D., Debontridder et al., Phys. Rev. Lett. 107, 097202 (2011).

[2] Brun, C., Serrier-Garcia L., Cren, T., et al., Phys. Rev. Lett. (2013) to appear.




Figure 1. STM-image (600nm x 600nm) of the studied system. The network consists of mono-atomic terraces of Si-substrate covered by non-superconducting wetting layer of Pb (in blue) and superconducting Pb-nano-islands few monolayer thick (green-yellow-orange). Rich island geometry provides a variety of landscapes confining quantum vortices.

Key-words: superconductivity at nanoscale, confinement in superconductivity, vortex network, giant vortex, proximity effect in superconductors, Josephson vortex, STM/STS